



## GENERAL DESCRIPTION

Junckers Strong Premium is a 1-component water-based and low odour lacquer for wooden floors in high traffic commercial areas.

The product is suitable for previously sealed as well as on new or sanded older floors.

When lacquering an untreated floor or floor sanded to bare wood, use one of Junckers primers prior to the finishing top seal.

## PRODUCT DESCRIPTION

**Product:** 1-component water-based polyurethane lacquer.

**Package sizes:** 5 litre.

**Appearance:** Creamy/milky in the container. Colourless film when dry.

**Gloss:** Ultra matt, Matt, Silk Matt.

## TECHNICAL DATA

**Coverage:** 10-12 m<sup>2</sup> per litre.

**Before application:** Stir or shake the lacquer well before use.

**Application tools:** Brush, roller, air/airless spray.  
Don't apply by pouring out the lacquer directly on the floor.

**Substrate temperature:** Minimum 15° C.

**Dilution:** Delivered ready for use. Dilution is not recommended.

**Drying time:**  
Approx. 3 hours at 20° C and 50 % RH. Fully cured after 72 hours.  
Apply only 2 coats of lacquer per day.

**RH:**  
Water-based products have a certain gluing effect and are therefore recommended only to be used in rooms with a stable humidity. This means that the difference between the highest and lowest relative humidity should not fluctuate more than 30 % over the year.

**Cleaning of tools:** Soap and water before drying of the lacquer.

**Storage:** Lasts for 1 year if unopened and stored at 20° C. Not to be exposed to temperatures below 0° C.

## SYSTEM RECOMMENDATIONS

### High traffic commercial areas:

1 coat of Junckers PreLak 8 m<sup>2</sup>/litre + 2 coats of Junckers Strong Premium 10 m<sup>2</sup>/litre  
or

1 coat of Junckers ProSeal 10 m<sup>2</sup>/litre + 2 coats of Junckers Strong Premium 10 m<sup>2</sup>/litre  
or

1 coat of Junckers BasePrime 10 m<sup>2</sup>/litre + 2 coats of Junckers Strong Premium 10 m<sup>2</sup>/litre.

## DIRECTION FOR USE

**Untreated/Sanded Floors:** Ensure that the surface is absolutely clean, dry and free from dust, wax, grease, polish, soap residues etc. Sand the surface to remove dirt and irregularities. Vacuum thoroughly and wipe off with a cloth well wrung in clean water.

Prime with one coat of Junckers PreLak, Junckers ProSeal or Junckers BasePrime. Leave to dry. Sand with 150-180 grit sandpaper along the fibres of the wood. Vacuum sanding dust and wipe off with a cloth well wrung in clean water.

Apply one coat of Junckers Strong Premium. Leave to dry overnight and then apply the finishing coat.

**Previously sealed floors:** Clean with Junckers SylvaNeutralizer. Sand thoroughly using grit 150-180. Vacuum sanding dust and wipe off with a cloth well wrung in clean water.

Trial applications should be conducted on a couple of spots, 2 coats at 4 hours interval. After drying for 24 hours check the spots for adhesion by scraping with the edge of a coin. If the adhesion is functioning and the appearance of the surface is acceptable, the floor can be sealed with one coat of Junckers Strong Premium.

If the trial application is not satisfactory, proceed as described under "Wax/Polish Treated floors".

**Wax/Polish treated Floors:** Machine sand by first using grit 24-36 to strip old coats. Then remove abrasion marks using grit 60-80. Finally, use grit 120-150 to obtain a completely smooth surface. Vacuum thoroughly. Treat the floor as described under "Untreated/ Sanded floors".

## IMPORTANT

Before using the product, read the label on the container carefully and observe the recommended precautionary measures. See Material Safety Data Sheet for detailed information.

## FURTHER INFORMATION

### Products:

- F 5.3 - Junckers PreLak
- F 6.4 - Junckers BasePrime
- F 8.6 - Junckers ProSeal
- F 10.3 - Junckers SylvaNeutralizer